

Manufacturing excellence



SuperEco

MR/EO

Customwood® SuperEco is an MDF product specially designed with MR (Moisture Resistance) properties and very low formaldehyde emission.



- **Moisture/humidity resistant**
- **Excellent mechanical properties**
- **Highly machinable**
- **Very low formaldehyde EO emission rating**

Customwood® SuperEco is typically used for general non-load bearing applications either in dry or humid interior conditions including:

- Kitchen cabinets
- Interior furniture
- Walls and ceilings
- Flooring substrates.

Customwood® SuperEco is a very low formaldehyde emitting MDF product and makes for an exceptional choice for use in any location and for many purposes, including residential houses, offices, schools, hospitals and government buildings.


Customwood®

 **Customwood**® also available...

ThinPanel

EO

ProPanel

EO

UltraLight

EO

SuperFinish

MR/SEO

This product information is only applicable to the New Zealand market, other countries please contact us for further information.

DAIKEN
NEW ZEALAND LIMITED

0800 369 633
info@customwood.co.nz
www.customwood.co.nz

Customwood®

Standard specifications

SuperEco

MR/EO

| Applicable to New Zealand market | ThinPanel (EO) | | | | ProPanel (EO) | | | | | | | | LightPanel (EO) | | | SuperEco (MR/EO) | | SuperFinish (MR/SEO) | | |
|---------------------------------------|--|-----|------|------|---------------|------|------|------|------|------|------|-----|-----------------|------|------|--|------|--|------|------|
| Formaldehyde Emissions | EO (≤ 0.5mg/litre) AS/NZ Standard test 4266.16 | | | | | | | | | | | | | | | EO (≤ 0.5mg/litre) AS/NZ Standard test 4266.16 | | SEO (< 0.3mg/litre) Comparable to JIS F★★★★ and USA California regulations for ultralow emission panels. | | |
| Mechanical Properties | Good, compliant to AS/NZS Standard for STD general purpose MDF | | | | | | | | | | | | | | | Excellent, very strong panel compliant to AS/NZ Standard for general purpose MR MDF. | | Excellent, very strong panel compliant to AS/NZ Standard for general purpose MR MDF. | | |
| Face Density | Good | | | | | | | | | | | | | | | Very good | | Excellent | | |
| Core Density and Machinability | Good | | | | | | | | | | | | | | | Very good | | Excellent | | |
| Surface Finish | Good | | | | | | | | | | | | | | | Very good | | Excellent | | |
| Fit-for-purpose | General non-load applications in dry interior conditions | | | | | | | | | | | | | | | General non-load applications in dry or humid interior conditions. Excellent machinability and strength. | | General non-load applications in dry or humid interior conditions. Excellent machinability and strength. Superior paint finish on faces and edges. | | |
| Thickness (mm) | 3 | 4 | 4.75 | 6 | 9 | 12 | 15 | 16 | 18 | 25 | 30 | 16 | 18 | 16 | 18 | 12 | 18 | 25 | | |
| Sheet Size (mm) | Please see size sheets | | | | | | | | | | | | | | | | | | | |
| Density (kg/m³) | 735-850 | | | | 650-750 | | | | | | | | 550-650 | | | 675-750 | | 650-730 | | |
| Weight Per Area* (kg/m²) | 2.3 | 3.2 | 3.7 | 4.8 | 6.5 | 8.6 | 10.7 | 11.4 | 12.2 | 16.5 | 18 | 9.6 | 10.8 | 11.6 | 13.1 | 8.8 | 13.1 | 17.5 | | |
| Internal Bond* (MPa) | 1.4 | | | | 0.9 | | | | | | | | 0.8 | 0.65 | 0.8 | 1.20 | | 1.40 | 1.30 | 1.20 |
| MOR* (MPa) | 36 | 40 | | | 32 | 35 | 33 | 35 | | 29 | 25 | | | 35 | 38 | 35 | 38 | 30 | | |
| Thickness Swell 24 Hours* (%) | 26 | 24 | | 18 | 13 | 10 | 8 | | 6.5 | 5 | 4.5 | 9 | 8 | 6 | 5.5 | 8 | 5 | 4.5 | | |
| MOE* (MPa) | 3500 | | | 3300 | 2600 | 3000 | 2800 | | | 2500 | 2400 | | | 3000 | | 3100 | 2400 | | | |
| Wet MOR* (MPa) | NA | | | | | | | | | | | | | | | 6 | | 7 | 8 | 5 |
| Thickness Tolerance* (mm) | | | | | | | | | | | | | | | | ±0.15 | | | | |
| Length and Width Tolerance* (mm) | | | | | | | | | | | | | | | | ±2.0 | | | | |
| Diagonals Difference Tolerance** (mm) | | | | | | | | | | | | | | | | ±3.0 | | | | |
| Bow Measurement Tolerance** (mm/m) | N/A | | | | | | | | | | | | 3.0 | | | 3.0 | | N/A | 3.0 | |
| Moisture Content Range** | 5-13% | | | | | | | | | | | | | | | | | | | |
| Bracing Ratings | P21 testing report by BRANZ is available. Please contact Daiken Customer Service for details and a copy of the report. | | | | | | | | | | | | | | | | | | | |
| Fire Classification NZBC C/VM2 | Fire Test Report by BRANZ is available. Please contact Daiken Customer Service for details and a copy of the report. | | | | | | | | | | | | | | | | | | | |

* Typical value of Customwood® measured at DNZ testing facilities. Daiken New Zealand guarantee that Customwood® should meet the minimum specifications on the properties described by AS/NZ 1859.2:2017

** Customwood® specification

Note on dimensional stability: MDF is made of wood and moisture is always present in wood. Furthermore, moisture will enter or leave wood products depending on environmental conditions like air temperature and relative humidity. As moisture enters or leaves, wood product properties and dimensions will change. Appropriate design and storage measures have to be taken to minimise MDF exposure to ambient changes and subsequent changes in dimensions and properties. In general, the impact of moisture changes in panel properties is minimal if the air relative humidity is maintained between 50% and 80%. In general, panels will expand (up to 3mm/m) if exposed to ambient air with more than 65%RH and will shrink (up to 3mm/m) if exposed to ambient air with less than 65% RH.



Furniture, Fittings and Flooring Licence No. 3210068



The mark of responsible forestry



Quality ISO 9001



Environment ISO 14001



Health & Safety ISO 45001

This product information is only applicable to the New Zealand market, other countries please contact us for further information.

DAIKEN
NEW ZEALAND LIMITED

0800 369 633
info@customwood.co.nz
www.customwood.co.nz